

**Adhesive Nairit T 3405 contact adhesive for bonding different materials. Excellent adhesion to metal. Very high temperature resistance. High strength instantly. Excellent adhesion to EVA elastomers.**

### AREAS OF APPLICATION.

Adhesive Nairit T 3405 specifically designed for bonding rubber, metal, leather, wood, chipboard, plastic (including plastic based in EVA). Not recommended for bonding polystyrene, polyolefins.

### PROPERTIES.

- High strength and good thermal stability of the assemblies.
- Resistance to hydrolysis (water resistance), acids and mineral oil.
- Good connection flexibility, including at low temperatures.
- Easy to apply.
- High adhesion to most bases.
- The mean open time, which allows high strength instantly.
- Short time for further increase in strength.

### TECHNICAL DATA.

Based	<i>CR\A rubber and synthetic resins in organic solvents</i>
Colour	<i>From light brown to brown</i>
Conventional solids content, %	<i>25 – 27</i>
Viscosity at 20°C, mPa.s	<i>approx. 600</i>
Density at 20 °C, g/cm <sup>3</sup>	<i>approx. 0.85</i>
Open time at 20 °C, min	<i>15</i>
Bond Strength, N/cm, 24 hour	<i>55 – 67</i>
The time to reach 70% of maximum strength, min	<i>7 - 10</i>
Temperature resistance of the assemblies (adhesive strength not less than 20 N/cm), °C	<i>120</i>
Maximum allowable operating temperature (short-term exposure), °C	<i>150</i>

### PACKAGING.

Metal can 620g (0,8L)	12 units in cardboard box
Conical metal container 2,3kg (3L)	4 units in cardboard box
Conical metal container 16,5kg (20L)	
Cylindrical metal container 40kg (50L)	

### STORAGE.

Storage time 12 months. Recommended storage temperature: 5 - 25 °C. Storage in original containers on distance from open flame.

### SAFETY.

Highly flammable and irritant.

This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updating of safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information relating

## Technical Datasheet

### Adhesive Nairit T 3405

to the current classification and labeling, applications and processing methods and further data Read material safety data sheet before use.

#### INSTRUCTIONS FOR USE.

##### **Substrates preparation:**

The surfaces should be sound, smooth, clean and dust-free. Surface may be painted (paint should hold well).

##### **Application :**

Apply a regular layer with a brush or spray application to each substrate. Recommended applying temperature is 18 – 22 °C, humidity 60 - 65%. For highly absorbent surfaces (such as chipboard, gypsum) are recommended double glue application with 10 minutes interval between each application. For non-absorbing – one glue application. Apply nearly 100 – 120 g of adhesive for each square meter.

##### **Drying:**

Adhesive film should be dried under natural conditions. Minimal drying time depends on temperature and usually near 8 – 12 minutes. The end of drying is easy to identify by touch – adhesive ceases to be tacky.

##### **Bonding:**

Press products to each other thermally activated adhesive films, and highly compressed (pressed) or rolled rollers. Leave under load is not needed.

Attention. The time between the by compressing and thermal activation must not exceed the open time - this glue - 15 minutes. After 7 - 10 minutes adhesive joint strength reaches 70% of its maximum. A further increase in strength occurs slowly during 30 - 40 hours.

The information contained in this document is correct as far as it possible to judge the data available at the date of publication. The information provided is intended only as a general technical information and is not considered a warranty or quality specification. The information relates only to this material and may be valid for such material to be used in combination with any other materials or in any process, unless it is mentioned in this document.

#### «HIMIK-PLUS»

str. Lisova, 4,  
Brovary Kiev region,  
Ukraine

Phone: +38 044 331-25-27

Fax: +38 044 587-89-03

Technological support: +38 044 331-25-28

[www.himik-plus.com](http://www.himik-plus.com)